

Sub B5  
cont.

(b) a component B that is at least one tackifier selected from the group consisting of petroleum resins, terpene resins, rosin resins, coumarone-indene resins, hydrogenated resins thereof, and modified resins thereof; and

A1

(c) 42-62 wt% of a component C that is a hydrocarbonic plasticizer, wherein said pressure sensitive sealant composition is prepared by mixing together 100 parts by weight of said component A, 20-60 parts by weight of said component B, and 150-400 parts by weight of said component C.

Sub C1

Claim 11 (new). A pressure sensitive sealant composition as claimed in claim 10, wherein said composition comprises 6-14 wt% of said component B.

Claim 12 (new). A pressure sensitive sealant composition as claimed in claim 10, wherein said composition comprises 25-30 wt% of said component A.

---